DISSIPATIVE PINK POLY



Specifications:

Electrical Properties	Typical Values	Test Procedures/Method
Static Decay	<1.0 sec.	ASTM 101 Method 4046
Surface Resistance	< 10^{11} Ohms	ESD S11.11
Polycarbonate Haze	NE	72 hr contact
Corrosivity Observations	NE	MIL-STD-3010, M3005
Physical Properties		
Thickness	4 mils	
Melt Index	0.050 gm/10 min	ASTM D-1238
Density	0.923 gm/cc	ASTM D-1505
Dart Impact	230 gms	ASTM D-1709
Coefficient of Friction	MD 24,000 psi	ASTM D-1894 (unmodified film)
1% Secant Modulus (Stiffness)	MD 25,000 psi	ASTM D-882

Item No.	Size (in.) W x L	Item No.	Size (in.) W x L
49100	2 x 3	49110	8 x 12
49101	3 x 4	49111	10 x 12
49102	3 x 5	49112	10 x 14
49103	4 x 6	49113	10 x 20
49104	5 x 7	49114	12 x 16
49105	5 x 8	49115	14 x 16
49106	6 x 8	49116	15 x 18
49107	6 x 9	49117	16 x 20
49108	6 x 10	49118	18 x 20
49109	8 x 10	49119	18 x 24
Packaged 100 per package			

RoHS Compliance Statement
None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1. See Protektive Pak Inc. letter on-line at ProtektivePak.com.

Made in America

TRANSPARENT STATIC DISSIPATIVE (PINK POLY)

PROTEKTIVE PAK

PROTEKTIVE PAK
13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE (909) 627-2578, FAX (909) 363-7331
ProtektivePak.com

DRAWING NUMBER 49100

DATE: 5/06

© 2006 DESCO INDUSTRIES INC.
Employee Owned