

DATA SHEET

TN27/15/11

Iron powder toroids

Supersedes data of September 2004

2008 Sep 01

Iron powder toroids

TN27/15/11

RING CORES (TOROIDS)

Effective core parameters


SYMBOL	PARAMETER	VALUE	UNIT
$\Sigma(l/A)$	core factor (C1)	1.02	mm^{-1}
V_e	effective volume	3720	mm^3
l_e	effective length	61.6	mm
A_e	effective area	60.4	mm^2
m	mass of core	≈ 25	g

Coating

The cores are coated with polyamide 11 (PA11), flame retardant in accordance with “UL 94V-2”; UL file number E 45228 (M).
The colour is white.
Maximum operating temperature is 160 °C.

Isolation voltage

DC isolation voltage: 1 500 V.
Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.



Ring core data

GRADE	A_L (nH)	μ_i	TYPE NUMBER
2P40 ^{sup}	$49 \pm 10\%$	≈ 40	TN27/15/11-2P40
2P50 ^{sup}	$62 \pm 10\%$	≈ 50	TN27/15/11-2P50
2P65 ^{sup}	$80 \pm 10\%$	≈ 65	TN27/15/11-2P65
2P80 ^{sup}	$94 \pm 10\%$	≈ 80	TN27/15/11-2P80
2P90 ^{sup}	$105 +10/-15\%$	≈ 90	TN27/15/11-2P90

Iron powder toroids

TN27/15/11

DATA SHEET STATUS DEFINITIONS

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

DISCLAIMER

Life support applications — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

PRODUCT STATUS DEFINITIONS

STATUS	INDICATION	DEFINITION
Prototype		These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.
Design-in		These products are recommended for new designs.
Preferred		These products are recommended for use in current designs and are available via our sales channels.
Support		These products are not recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.