
Creation Date : July 29, 2019 (GMT)

Ferrite Magnets

FB3N

Lead Free

Series	FB
Material Name	FB3
Feature	General material
Application	Sensor Application
Status	Production



Magnetic Characteristics	
Residual Magnetic Flux Density [Br] / mT	395 ±15
Coercive Force [Hcb] / (kA / m)	234.8 ±12
Coercive Force [Hcj] / (kA / m)	238.7 ±16
Maximum Energy Product [BH] / (kJ / m³)	28.7

! Images are for reference only and show exemplary products.
! This PDF document was created based on the data listed on the TDK Corporation website.
! All specifications are subject to change without notice.

Copyright(c) TDK Corporation. All rights reserved.