

February, 2015

3M™ Self-Extinguishing Hot Melt Adhesive 3748 VO

Product Description

3M™ Hot Melt Adhesive 3748 VO is a tough, flexible, thermoplastic hot melt, 100% solids adhesive which exhibits good peel adhesion and thermal shock properties along with higher heat resistance. It features excellent electrical properties which make it ideal for use on printed wiring board and other electronic bonding applications.

Hot Melt Adhesive 3748 VO is self-extinguishing and has a UL 94 VO rating. In addition to electronic applications, it is also useful in many general industrial bonding and sealing applications where a self-extinguishing characteristic is required.

Product Features

- Excellent Adhesion
- Good Electrical Properties
- Non Corrosive to Metal



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Property	Values	Notes
Color	Light Yellow	Colors may vary from nearly white to yellow/amber. Adhesive performance is not affected by color variation.
Base Resin	Polyolefin	

Typical Cured Characteristics

Shore D Hardness: 26

Conditions
Dwell/Cure Time: 60 min @ Room Temperature
Methods
ASTM D2240

Typical Performance Characteristics

Solvent Resistance	Environmental Condition
A	Immersed in Acetone one hour
B	Immersed in Acetone 30 days
A	Immersed in Isopropyl Alcohol one hour
B	Immersed in Isopropyl Alcohol 30 days
B	Immersed in Freon TF one hour
C	Immersed in Freon TF 30 days
B	Immersed in Freon TMC one hour
C	Immersed in Freon TMC 30 days
B	Immersed In 1, 1, 1 - Trichloroethane one hour
C	Immersed In 1, 1, 1 - Trichloroethane 30 days
A	Immersed in RMA Flux one hour
B	Immersed in RMA Flux 30 days

Property: Solvent Resistance
notes: A = No attack B = Slight Surface Attack/Softness C = Severe Attack/Breakup

Typical Performance Characteristics (continued)

Overlap Shear Strength	Substrate
215 lb/in²	FR-4 to FR-4
275 lb/in²	Fir to Fir
250 lb/in²	Polypropylene to Polypropylene
220 lb/in²	Polyethylene to Polyethylene

Property: Overlap Shear Strength
 Method: 3M C3096
 notes: 1" x 4" Douglas Fir specimens are bonded with hot melt adhesive using a 1" overlap and 13 mil wire spacer to set bond line thickness. Bonds are then conditioned for 24 hours at 70°F (22°C), 50% relative humidity before testing. Bonds are pulled in shear at a separation bond speed of 2 inch a minute recording strength at failure.

180° Peel Adhesion	Substrate
608 oz/in	Wire Mesh to FR-4
560 oz/in	Wire Mesh to Polypropylene
432 oz/in	Wire Mesh to Polyethylene
416 oz/in	Wire Mesh to Fir

Property: 180° Peel Adhesion
 Method: 3M C3168
 notes: Test involves bonding .020 in wire mesh (galvanized window screen type) to substrate using hot melt adhesive. Wire mesh is encapsulated with adhesive. After conditioning, bond is tested by 180° peel back method using Instron at 10 inches per minute peel speed.

Weight Loss by TMA (In Air)	Test Condition
1 %	459°F (237°C)
5 %	621°F (327°C)
10 %	673°F (356°C)

Property: Weight Loss by TMA (In Air)
 notes: Temperature of weight loss at 5°C/min

Property	Values		Method	Notes	Test Condition
Two Pound Dead Load Heat Resistance	79 °C	175 °F	3M C3093	1" x 4" Douglas Fir specimens are bonded with hot melt adhesive using a 1" overlap shear configuration. Bonds are then conditioned for 24 hours at 70°F (22°C), 50% relative humidity before testing. Bonds are subjected to 2 lbs. per square inch load at 100°F (49°C) for 30 minutes. Temperature of the bond line is raised every 30 minutes until failure. Heat resistance recorded is the last temperature prior to bond failure.	
Thermal Shock Resistance	Passes 5 cycles w/o cracking		3M C3167	Potted Washer Olyphant test	100°C (air) to -40°C (liquid)

Electrical and Thermal Properties

Dielectric Constant	Test Condition
2.3	10 KHz, Room Temperature
2.3	100 KHz, Room Temperature
2.3	1 KHz, Room Temperature
0.001	1MHz, Room Temperature
2.3	100 Hz, Room Temperature
2.3	100 MHz, Room Temperature

Property: Dielectric Constant
Method: ASTM D150

Dissipation Factor	Test Condition
0.001	10 KHz, Room Temperature
0.001	100 KHz, Room Temperature
0.001	1 KHz, Room Temperature
0.002	100 Hz, Room Temperature
0.001	100 MHz, Room Temperature

Property: Dissipation Factor
Method: ASTM D150

Thermal Conductivity				
19.2 W/m/K	1.92×10^{-3} J/cm - sec - °C	1.1×10^{-1} (btu-ft)/(h-ft²-°F)	4.58×10^{-4} Cal/s/cm/°C	6×10^{17} W/m/K

Property: Thermal Conductivity
Test Condition : 107°F (41°C)
notes: On .020" samples

Property	Values	Method	Notes	Test Condition
Dielectric Strength	2.3 V/μm			
Dielectric Strength	1400 V/mil	ASTM D149	11 mil sample	
Volume Resistivity	4.5×10^{17} Ω-cm	ASTM D257		Room Temperature
Coefficient of Thermal Expansion	-34×10^{-6} m/m/°C		By TMA	-100 - -40°C
Coefficient of Thermal Expansion	154.5×10^{-6} m/m/°C		By TMA	-20 - 25°C

3M™ Self-Extinguishing Hot Melt Adhesive 3748 VO

Typical Physical Properties

Viscosity	Test Condition
8500 cP	356°F(180°C)
5000 cP	392°F(200°C)
3300 cP	428°F(220°C)

Property: Viscosity

Property	Values	
Specific Gravity	1.09	
Ball & Ring Softening Point	152 °C	305 °F
UL Listing	UL 94 - VO	

Handling/Application Information

Application Equipment

- 3M™ Hot Melt Applicator TC or TCQ
- 3M™ Hot Melt Applicator EC - Temperature Module #4
- 3M™ Hot Melt Applicator PG II

Storage and Shelf Life

Store below 120°F (49°C).
When stored at the recommended conditions, this product has a shelf life of 24 months from the date of manufacture.

Industry Specifications

UL 94 - VO

Trademarks

3M is a trademark of 3M.
Freon is a registered trademark of E.I. DuPont de Nemours Co.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~ /3M-Hot-Melt-Adhesive-3748-VO?N=5002385+3293241784&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=3748 VO

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

3M™ Self-Extinguishing Hot Melt Adhesive 3748 VO

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.



3M United States
3M Center
St. Paul, MN 55144-1000
800-362-3550
www.3M.com

Please recycle.
© 3M 2021. All Rights Reserved.

The brands listed above are trademarks of 3M