**NICHIA CORPORATION** 

# **SPECIFICATIONS FOR LED**

# NESB146AT-N3

- Pb-free Reflow Soldering Application
- Built-in ESD Protection Device
- RoHS Compliant
- ISO/TS16949 Compliant



## **SPECIFICATIONS**

(1) Absolute Maximum Ratings

Item	Symbol	Absolute Maximum Rating	Unit
Forward Current	${ m I}_{\sf F}$	30	mA
Pulse Forward Current	$I_{\sf FP}$	100	mA
Allowable Reverse Current	${ m I}_{ m R}$	85	mA
Power Dissipation	$P_{D}$	105	mW
Operating Temperature	$T_{opr}$	-40~110	°C
Storage Temperature	$T_{stg}$	-40~110	°C
Junction Temperature	T,	125	°C

<sup>\*</sup> Absolute Maximum Ratings at  $T_A=25$ °C.

(2) Initial Electrical/Optical Characteristics

2) Tilled Electrical Optical Characteristics						
Item		Symbol	Condition	Тур	Max	Unit
Forward Voltage		$V_{F}$	I <sub>F</sub> =20mA	3.2	-	V
Luminous Intensity		$I_{v}$	I <sub>F</sub> =20mA	900	-	mcd
x		-	I <sub>F</sub> =20mA	0.19	-	-
Chromaticity Coordinate	у	-	I <sub>F</sub> =20mA	0.29	-	-
Thermal Resistance		R <sub>0JS real</sub>	-	-	161	°C/W
		R <sub>0JS el</sub>	-	-	134	°C/W

<sup>\*</sup> Characteristics at  $T_A=25$ °C.

<sup>\*</sup>  $I_{\text{FP}}$  conditions with pulse width  $\leq 10 \text{ms}$  and duty cycle  $\leq 10 \%$ .

<sup>\*</sup> Luminous Intensity value as per CIE 127:2007 standard.

<sup>\*</sup> Chromaticity Coordinates as per CIE 1931 Chromaticity Chart.

<sup>\*</sup> Thermal resistance values ( $R_{\theta JS\_real}$ ) determined by considering the energy conversion efficiency( $\eta_e = 17\%$ ). Refer to JESD51.

# RANKS

Item	Rank	Min	Max	Unit
Forward Voltage	-	2.8	3.5	V
	Cd1200	1200	1440	
	Cd1000	1000	1200	
	Cd860	860	1000	
Luminous Intensity	Cd720	720	860	mcd
	Cd600	600	720	
	Cd500	500	600	

Color Ranks

	Rank Ai1			
х	0.1550	0.1589	0.1677	0.1637
У	0.2149	0.2306	0.2296	0.2139

	Rank Ai3				
x	0.1696	0.1735	0.1823	0.1784	
٧	0.2132	0.2290	0.2280	0.2122	

	Rank Ai5				
х	0.1842	0.1882	0.1969	0.1930	
У	0.2116	0.2273	0.2264	0.2106	

	Rank Bi2				
х	0.1677	0.1716	0.1775	0.1735	
У	0.2296	0.2454	0.2447	0.2290	

		Rank Bi4				
	х	0.1823	0.1862	0.1921	0.1882	
Ī	У	0.2280	0.2437	0.2431	0.2273	

	Rank Ci1			
x	0.1628	0.1668	0.1756	0.1716
у	0.2464	0.2621	0.2611	0.2454

	Rank Ci3				
х	0.1775	0.1814	0.1902	0.1862	
У	0.2447	0.2605	0.2595	0.2437	

	Rank Ci5			
х	0.1921	0.1960	0.2048	0.2009
У	0.2431	0.2588	0.2579	0.2421

	Rank Di2				
х	0.1756	0.1795	0.1853	0.1814	
У	0.2611	0.2769	0.2762	0.2605	

	Rank Di4			
Х	0.1902	0.1941	0.2000	0.1960
У	0.2595	0.2753	0.2746	0.2588

	Rank Ai2				
Х	0.1637	0.1677	0.1735	0.1696	
V	0.2139	0.2296	0.2290	0.2132	

	Rank Ai4				
х	0.1784	0.1823	0.1882	0.1842	
У	0.2122	0.2280	0.2273	0.2116	

	Rank Bi1				
Х	0.1589	0.1628	0.1716	0.1677	
у	0.2306	0.2464	0.2454	0.2296	

	Rank Bi3				
X	0.1735	0.1775	0.1862	0.1823	
٧	0.2290	0.2447	0.2437	0.2280	

	Rank Bi5				
Х	0.1882	0.1921	0.2009	0.1969	
У	0.2273	0.2431	0.2421	0.2264	

	Rank Ci2				
Х	0.1716	0.1756	0.1814	0.1775	
У	0.2454	0.2611	0.2605	0.2447	

	Rank Ci4				
Х	0.1862	0.1902	0.1960	0.1921	
У	0.2437	0.2595	0.2588	0.2431	

	Rank Di1				
X	0.1668	0.1707	0.1795	0.1756	
У	0.2621	0.2779	0.2769	0.2611	

	Rank Di3				
Х	0.1814	0.1853	0.1941	0.1902	
У	0.2605	0.2762	0.2753	0.2595	

	Rank Di5				
Х	0.1960	0.2000	0.2087	0.2048	
У	0.2588	0.2746	0.2736	0.2579	

	Rank Ei1			
Х	0.1707	0.1746	0.1834	0.1795
У	0.2779	0.2936	0.2926	0.2769

	Rank Ei2				
Х	0.1795	0.1834	0.1893	0.1853	
У	0.2769	0.2926	0.2920	0.2762	

	Rank Ei3				
Х	0.1853	0.1893	0.1980	0.1941	
У	0.2762	0.2920	0.2910	0.2753	

	Rank Ei4			
x	0.1941	0.1980	0.2039	0.2000
У	0.2753	0.2910	0.2904	0.2746

	Rank Ei5				
Х	0.2000	0.2039	0.2127	0.2087	
У	0.2746	0.2904	0.2894	0.2736	

	Rank Fi1				
x	0.1746	0.1786	0.1874	0.1834	
У	0.2936	0.3094	0.3084	0.2926	

	Rank Fi2				
Х	0.1834	0.1874	0.1932	0.1893	
У	0.2926	0.3084	0.3078	0.2920	

	Rank Fi3				
х	0.1893	0.1932	0.2020	0.1980	
У	0.2920	0.3078	0.3068	0.2910	

	Rank Fi4				
x	0.1980	0.2020	0.2078	0.2039	
У	0.2910	0.3068	0.3061	0.2904	

	Rank Fi5				
x	0.2039	0.2078	0.2166	0.2127	
У	0.2904	0.3061	0.3051	0.2894	

	Rank Gi1				
х	0.1786	0.1825	0.1913	0.1874	
у	0.3094	0.3252	0.3242	0.3084	

	Rank Gi2			
х	0.1874	0.1913	0.1971	0.1932
У	0.3084	0.3242	0.3235	0.3078

	Rank Gi3				
X	0.1932	0.1971	0.2059	0.2020	
V	0.3078	0.3235	0.3225	0.3068	

	Rank Gi4			
Х	0.2020	0.2059	0.2118	0.2078
У	0.3068	0.3225	0.3219	0.3061

	Rank Gi5			
х	0.2078	0.2118	0.2205	0.2166
у	0.3061	0.3219	0.3209	0.3051

<sup>\*</sup> Ranking at  $T_A=25$ °C.


The rank combination ratio per shipment will be decided by Nichia.

<sup>\*</sup> Forward Voltage Tolerance:  $\pm 0.05V$ 

<sup>\*</sup> Luminous Intensity Tolerance:  $\pm 5\%$ 

<sup>\*</sup> Chromaticity Coordinate Tolerance: ±0.003

 $<sup>\</sup>boldsymbol{\ast}$  LEDs from the above ranks will be shipped.




# **OUTLINE DIMENSIONS**


- \* 本製品はRoHS指令に適合しております。 This product complies with RoHS Directive.
- \* 括弧で囲まれた寸法は参考値です。 The dimension(s) in parentheses are for reference purposes.


NxSB146A-Nx 管理番号 No. STS-DA7-9564

(単位 Unit: mm, 公差 Tolerance: ±0.1)











項目 Item	内容 Description	
パッケージ材質 Package Materials	耐熱性ポリマー Heat-Resistant Polymer	
封止樹脂材質 Encapsulating Resin Materials	シリコーン樹脂 (拡散剤+蛍光体入り) Silicone Resin (with diffuser and phosphor)	
電極材質 Electrodes Materials	銅合金+金メッキ Au-plated Copper Alloy	
質量 Weight	0.0051g(TYP)	

\* バリは寸法に含まないものとします。 Dimensions do not include mold flash or metal burr.



### **SOLDERING**


• Recommended Reflow Soldering Condition(Lead-free Solder)



• Recommended Hand Soldering Condition

Temperature	350°C Max
Soldering Time	3sec Max

• Recommended Soldering Pad Pattern



(単位 Unit: mm)

- \* This LED is designed to be reflow soldered on to a PCB. If dip soldered, Nichia cannot guarantee its reliability.
- \* Reflow soldering must not be performed more than twice. Hand soldering must not be performed more than once.
- \* Avoid rapid cooling. Ramp down the temperature gradually from the peak temperature.
- \* Nitrogen reflow soldering is recommended. Air flow soldering conditions can cause optical degradation, caused by heat and/or atmosphere.
- \* Since the silicone used in the encapsulating resin is soft, do not press on the encapsulant resin.


  Pressure can cause nicks, chip-outs, encapsulant delamination and deformation, and wire breaks, decreasing reliability.
- \* Repairing should not be done after the LEDs have been soldered. When repairing is unavoidable, a double-head soldering iron should be used.


It should be confirmed beforehand whether the characteristics of the LEDs will or will not be damaged by repairing.

- \* When soldering, do not apply stress to the LED while the LED is hot.
- \* When using a pick and place machine, choose an appropriate nozzle for this product. Using a pick-and-place nozzle with a smaller diameter than the size of the LED's emitting surface will cause damage to the emitting surface and may also cause the LED not to illuminate.
- \* The recommended soldering pad pattern is designed for attachment of the LED without problems.


  When precise mounting accuracy is required, such as high-density mounting, ensure that the size and shape of the pad are suitable for the circuit design.
- \* Consider factors such as the reflow soldering temperature, hand soldering temperature, etc. when choosing the solder.
- \* When flux is used, it should be a halogen free flux. Ensure that the manufacturing process is not designed in a manner where the flux will come in contact with the LEDs.
- \* Make sure that there are no issues with the type and amount of solder that is being used.

### TAPE AND REEL DIMENSIONS





### リール部 Reel



- \* 数量は1リールにつき 4500個入りです。
  - Reel Size: 4500pcs
- \* 実装作業の中断などでエンボスキャリアテープをリールに巻き取る場合、 エンボスキャリアテープを強く(10N以上)締めないで下さい。 LEDがカバーテープに貼り付く可能性があります。


When the tape is rewound due to work interruptions, no more than 10N should be applied to the embossed carrier tape.

The LEDs may stick to the top cover tape.


\* JIS C 0806電子部品テーピングに準拠しています。
The tape packing method complies with JIS C 0806
(Packaging of Electronic Components on Continuous Tapes).

### PACKAGING - TAPE & REEL

シリカゲルとともにリールをアルミ防湿袋に入れ、熱シールにより封をします。 Reels are shipped with desiccants in heat-sealed moisture-proof bags. Nxxxxxxx 管理番号 No. STS-DA7-0006C



アルミ防湿袋を並べて入れ、ダンボールで仕切ります。 Moisture-proof bags are packed in cardboard boxes with corrugated partitions.



un-ranked products.

- \* 本製品はテーピングしたのち、輸送の衝撃から保護するためダンボールで梱包します。
  Products shipped on tape and reel are packed in a moisture-proof bag.
  They are shipped in cardboard boxes to protect them from external forces during transportation.
- \* 取り扱いに際して、落下させたり、強い衝撃を与えたりしますと、製品を損傷させる原因になりますので注意して下さい。 Do not drop or expose the box to external forces as it may damage the products.
- \* ダンボールには防水加工がされておりませんので、梱包箱が水に濡れないよう注意して下さい。 Do not expose to water. The box is not water-resistant.
- \* 輸送、運搬に際して弊社よりの梱包状態あるいは同等の梱包を行って下さい。
  Using the original package material or equivalent in transit is recommended.

# LOT NUMBERING CODE

Lot Number is presented by using the following alphanumeric code.

YMxxxx - RRR

Y - <u>Year</u>

Year	Y
2015	F
2016	G
2017	Н
2018	I
2019	J
2020	K

M - Month


Month	М	Month	М
1	1	7	7
2	2	8	8
3	3	9	9
4	4	10	А
5	5	11	В
6	6	12	С

xxxx-Nichia's Product Number


RRR-Ranking by Color Coordinates, Ranking by Luminous Intensity

NESB146A-Nx 管理番号 No. STS-DA7-8780A

周囲温度-許容順電流特性 Ambient Temperature vs Allowable Forward Current




はんだ接合部温度(カソード側)-許容順電流特性 Solder Temperature(Cathode Side) vs Allowable Forward Current




# デューティー比-許容順電流特性


Duty Ratio vs Allowable Forward Current



# OPTICAL CHARACTERISTICS

\* 本特性は参考です。 All characteristics shown are for reference only and are not guaranteed. NESB146A-N3 管理番号 No. STS-DA7-8798B







# FORWARD CURRENT CHARACTERISTICS / TEMPERATURE CHARACTERISTICS

\* 本特性は参考です。 All characteristics shown are for reference only and are not guaranteed.


NESB146A-N3 管理番号 No. STS-DA7-8799B








順電流-相対光度特性 **Forward Current vs Relative Luminosity** 



周囲温度-相对光度特性 **Ambient Temperature vs** 



# FORWARD CURRENT CHARACTERISTICS / TEMPERATURE CHARACTERISTICS

\* 本特性は参考です。 All characteristics shown are for reference only and are not guaranteed. NESB146A-N3 管理番号 No. STS-DA7-8800A

順電流-色度 特性
Forward Current vs
Chromaticity Coordinate

0.31

0.30

> 0.29

100mA
30mA
20mA
1mA

0.28

0.18


0.19

х

0.20

0.21

0.17



# **RELIABILITY**

### (1) Tests and Results

Test	Reference Standard	Test Conditions	Test Duration	Failure Criteria #	Units Failed/Tested
Resistance to Soldering Heat (Reflow Soldering)	JEITA ED-4701 300 301	T <sub>sld</sub> =260°C, 10sec, 2reflows		#1	0/22
Solderability (Reflow Soldering)	JEITA ED-4701 303 303A	T <sub>sld</sub> =245±5°C, 5sec, Lead-free Solder(Sn-3.0Ag-0.5Cu)		#3	0/22
Thermal Shock	JEITA ED-4701 300 307	-40°C to 110°C, 1min dwell, 10sec transfer	100cycles	#1	0/100
Temperature Cycle	JEITA ED-4701 100 105	-40°C(30min)~25°C(5min)~ 110°C(30min)~25°C(5min)	100cycles	#1	0/100
Moisture Resistance (Cyclic)	JEITA ED-4701 200 203	25°C~65°C~-10°C, 90%RH, 24hr per cycle	10cycles	#1	0/100
High Temperature Storage	JEITA ED-4701 200 201	T <sub>A</sub> =110°C 1000hours		#1	0/100
Temperature Humidity Storage	JEITA ED-4701 100 103	T <sub>A</sub> =60°C, RH=90%	1000hours	#1	0/100
Low Temperature Storage	JEITA ED-4701 200 202	T <sub>A</sub> =-40°C	1000hours	#1	0/100
Room Temperature Operating Life		T <sub>A</sub> =25°C, I <sub>F</sub> =30mA Test board: See NOTES below	1000hours	#2	0/100
High Temperature Operating Life		T <sub>A</sub> =85°C, I <sub>F</sub> =25mA Test board: See NOTES below	1000hours	#2	0/100
Temperature Humidity Operating Life		$60$ °C, RH=90%, $I_F$ =20mA Test board: See NOTES below	1000hours	#2	0/100
Low Temperature Operating Life		$T_A$ =-40°C, $I_F$ =20mA Test board: See NOTES below		#2	0/100
Permanence of Marking	JEITA ED-4701 500 501	Isopropyl Alcohol, 23±5°C, Dipping Time: 5min	1time	#1	0/22
Vibration	JEITA ED-4701 400 403	200m/s², 100~2000~100Hz, 4cycles, 4min, each X, Y, Z	48minutes	#1	0/10
Free Fall		3drops from a height of 75cm		#1	0/10
Electrostatic Discharges	JEITA ED-4701 300 304	HBM, 2kV, $1.5k\Omega$ , $100pF$ , $3pulses$ , alternately positive or negative		#1	0/22

#### NOTES:

- 1) Test board: FR4 board thickness=1.6mm, copper layer thickness=35 $\mu$ m, R<sub> $\theta$ JA</sub> $\approx$ 320°C/W
- 2) Measurements are performed after allowing the LEDs to return to room temperature.

### (2) Failure Criteria

Criteria #	Items	Conditions	Failure Criteria
	Forward Voltage(V <sub>F</sub> )	I <sub>F</sub> =20mA	>U.S.L.×1.1
#1	Luminous Intensity(I <sub>V</sub> )	I <sub>F</sub> =20mA	<l.s.l.×0.7< td=""></l.s.l.×0.7<>
	Forward Voltage(V <sub>F</sub> )	I <sub>F</sub> =20mA	>U.S.L.×1.1
#2	Luminous Intensity(I <sub>V</sub> )	I <sub>F</sub> =20mA	<l.s.l.×0.5< td=""></l.s.l.×0.5<>
#3	Solderability	-	Less than 95% solder coverage

 $\hbox{U.S.L.}: \hbox{Upper Specification Limit} \qquad \hbox{L.S.L.}: \hbox{Lower Specification Limit}$ 

### **CAUTIONS**


(1) Storage


Conditions		Temperature	Humidity	Time
	Before Opening Aluminum Bag	≤30°C	≤90%RH	Within 1 Year from Delivery Date
Storage	After Opening Aluminum Bag	≤30°C	≤70%RH	≤4weeks
Baking		65±5°C	-	≥24hours

- Product complies with JEDEC MSL 2a or equivalent. See IPC/JEDEC STD-020 for moisture-sensitivity details.
- Absorbed moisture in LED packages can vaporize and expand during soldering, which can cause interface delamination and result in optical performance degradation. Products are packed in moisture-proof aluminum bags to minimize moisture absorption during transportation and storage.
  - Included silica gel desiccants change from blue to red if moisture had penetrated bags.
- After opening the moisture-proof aluminum bag, the products should go through the soldering process within the range of the conditions stated above. Unused remaining LEDs should be stored with silica gel desiccants in a hermetically sealed container, preferably the original moisture-proof bags for storage.
- After the "Period After Opening" storage time has been exceeded or silica gel desiccants are no longer blue, the products should be baked. Baking should only be done once.
- Although the leads or electrode pads (anode and cathode) of the product are plated with gold,
  prolonged exposure to a corrosive environment might cause the gold plated the leads or electrode pads to tarnish,
  and thus leading to difficulties in soldering. If unused LEDs remain, they must be stored in a hermetically sealed container.
   Nichia recommends using the original moisture-proof bag for storage.
- Do not use sulfur-containing materials in commercial products. Some materials, such as seals and adhesives, may contain sulfur. The contaminated plating of LEDs might cause an open circuit. Silicone rubber is recommended as a material for seals. Bear in mind, the use of silicones may lead to silicone contamination of electrical contacts inside the products, caused by low molecular weight volatile siloxane.
- To prevent water condensation, please avoid large temperature and humidity fluctuations for the storage conditions.
- Do not store the LEDs in a dusty environment.
- Do not expose the LEDs to direct sunlight and/or an environment where the temperature is higher than normal room temperature.

#### (2) Directions for Use

When designing a circuit, the current through each LED must not exceed the Absolute Maximum Rating.
 Operating at a constant current per LED is recommended. In case of operating at a constant voltage, Circuit B is recommended.
 If the LEDs are operated with constant voltage using Circuit A, the current through the LEDs may vary due to the variation in Forward Voltage characteristics of the LEDs.





- This product should be operated using forward current. Ensure that the product is not subjected to either forward or reverse voltage while it is not in use. In particular, subjecting it to continuous reverse voltage may cause migration, which may cause damage to the LED die. When used in displays that are not used for a long time, the main power supply should be switched off for safety.
- It is recommended to operate the LEDs at a current greater than 10% of the sorting current to stabilize the LED characteristics.
- Ensure that excessive voltages such as lightning surges are not applied to the LEDs.
- For outdoor use, necessary measures should be taken to prevent water, moisture and salt air damage.

### (3) Handling Precautions

- Do not handle the LEDs with bare hands as it will contaminate the LED surface and may affect the optical characteristics: it might cause the LED to be deformed and/or the wire to break, which will cause the LED not to illuminate.

  The lead could also cause an injury.
- When handling the product with tweezers, be careful not to apply excessive force to the resin.
   Otherwise, The resin can be cut, chipped, delaminate or deformed, causing wire-bond breaks and catastrophic failures.
- Dropping the product may cause damage.
- Do not stack assembled PCBs together. Failure to comply can cause the resin portion of the product to be cut, chipped, delaminated and/or deformed. It may cause wire to break, leading to catastrophic failures.

#### (4) Design Consideration

- PCB warpage after mounting the products onto a PCB can cause the package to break.
  - The LED should be placed in a way to minimize the stress on the LEDs due to PCB bow and twist.
- The position and orientation of the LEDs affect how much mechanical stress is exerted on the LEDs placed near the score lines.

  The LED should be placed in a way to minimize the stress on the LEDs due to board flexing.
- Board separation must be performed using special jigs, not using hands.

### (5) Electrostatic Discharge (ESD)

• The products are sensitive to static electricity or surge voltage. ESD can damage a die and its reliability.

When handling the products, the following measures against electrostatic discharge are strongly recommended:

Eliminating the charge

Grounded wrist strap, ESD footwear, clothes, and floors

Grounded workstation equipment and tools

ESD table/shelf mat made of conductive materials

- Ensure that tools (e.g. soldering irons), jigs and machines that are being used are properly grounded and that proper grounding techniques are used in work areas. For devices/equipment that mount the LEDs, protection against surge voltages should also be used.
- If tools or equipment contain insulating materials such as glass or plastic,

the following measures against electrostatic discharge are strongly recommended:

Dissipating static charge with conductive materials

Preventing charge generation with moisture

Neutralizing the charge with ionizers

• The customer is advised to check if the LEDs are damaged by ESD

when performing the characteristics inspection of the LEDs in the application.

Damage can be detected with a forward voltage measurement or a light-up test at low current ( $\leq 1$ mA).

• ESD damaged LEDs may have current flow at a low voltage or no longer illuminate at a low current.

Failure Criteria:  $V_F$ <2.0V at  $I_F$ =0.5mA

#### (6) Thermal Management

- Proper thermal management is an important when designing products with LEDs. LED die temperature is affected by PCB thermal resistance and LED spacing on the board. Please design products in a way that the LED die temperature does not exceed the maximum Junction Temperature (T<sub>J</sub>).
- ullet Drive current should be determined for the surrounding ambient temperature ( $T_A$ ) to dissipate the heat from the product.

### (7) Cleaning

- The LEDs should not be cleaned with water, benzine, and/or thinner.
- If required, isopropyl alcohol (IPA) should be used. Other solvents may cause premature failure to the LEDs due to the damage to the resin portion. The effects of such solvents should be verified prior to use.

  In addition, the use of CFCs such as Freon is heavily regulated.
- When dust and/or dirt adheres to the LEDs, soak a cloth with Isopropyl alcohol (IPA), then squeeze it before wiping the LEDs.
- Ultrasonic cleaning is not recommended since it may have adverse effects on the LEDs depending on the ultrasonic power and how LED is assembled.

If ultrasonic cleaning must be used, the customer is advised to make sure the LEDs will not be damaged prior to cleaning.

#### (8) Eye Safety

- In 2006, the International Electrical Commission (IEC) published IEC 62471:2006 Photobiological safety of lamps and lamp systems, which added LEDs in its scope.
  - On the other hand, the IEC 60825-1:2007 laser safety standard removed LEDs from its scope.
  - However, please be advised that some countries and regions have adopted standards
  - based on the IEC laser safety standard IEC 60825-1:20112001, which still includes LEDs in its scope.
  - Most of Nichia's LEDs can be classified as belonging into either the Exempt Group or Risk Group 1.
  - High-power LEDs, that emit light containing blue wavelengths, may be classified as Risk Group 2.
  - Please proceed with caution when viewing directly any LEDs driven at high current, or viewing LEDs with optical instruments which may greatly increase the damages to your eyes.
- Viewing a flashing light may cause eye discomfort. When incorporating the LED into your product, please be careful to avoid adverse effects on the human body caused by light stimulation.

#### (9) Others

- This product is intended to be used for general lighting, household appliances, electronic devices (e.g. mobile communication devices) and automobiles; it is not designed or manufactured for use in applications that require safety critical functions (e.g. aircraft, combustion equipment, life support systems, nuclear reactor control system, safety devices, spacecraft, submarine repeaters, traffic control equipment, trains, vessels, etc.). If the LEDs are planned to be used for these applications, unless otherwise detailed in the specification, Nichia will neither guarantee that the product is fit for that purpose nor be responsible for any resulting property damage, injuries and/or loss of life/health.
- The customer shall not reverse engineer by disassembling or analysis of the LEDs without having prior written consent from Nichia. When defective LEDs are found, the customer shall inform Nichia directly before disassembling or analysis.
- The specifications and appearance of this product may change without notice;

  Nichia does not guarantee the contents of this specification. Both the customer and Nichia

  will agree on the official specifications of supplied products before the volume production of a program begins.