

DATA SHEET

SURFACE-MOUNT CERAMIC MULTILAYER CAPACITORS

Mid-voltage: NP0/X7R
(Pb Free & RoHS compliant)

100 V TO 500 V

10 pF to 470 nF



SCOPE

This specification describes Mid-voltage NP0/X7R series chip capacitors with lead-free terminations.

APPLICATIONS

- PCs, hard disk, game PCs
- Power supplies
- LCD panel
- ADSL, modem

FEATURES

- Supplied in tape on reel
- Nickel-barrier end termination

ORDERING INFORMATION

Part number is identified by the series, size, tolerance, packing style, TC material, rated voltage and capacitance value.

YAGEO ORDERING CODE

CC XXXX X X XXX X **B** X XXX
 (1) (2) (3) (4) (5) (6) (7)

(1) SIZE – INCH BASED (METRIC)

0603 (1608)

0805 (2012)

1206 (3216)

1210 (3225)

1808 (4520)

1812 (4532)

(2) TOLERANCE

J = $\pm 5\%$

K = $\pm 10\%$

(3) PACKING STYLE

R = 7" paper tape

K = 7" blister tape

P = 13" paper tape

F = 13" blister tape

C = Bulk case

(4) TC MATERIAL

NP0

X7R

(5) RATED VOLTAGE

0 = 100 V

A = 200 V

Y = 250 V

B = 500 V

(6) PROCESS

B = BME

N = NME

(7) CAPACITANCE VALUE:

First two for significant figures and 3rd for number of zero

Letter "R" for decimal point

CONSTRUCTION

The capacitor consists of a rectangular block of ceramic dielectric in which a number of interleaved metal electrodes are contained. This structure gives rise to a high capacitance per unit volume.

The inner electrodes are connected to the two end terminations and finally covered with a layer of plated tin (NiSn). The terminations are lead-free. A cross section of the structure is shown in Fig. 1.




Fig. 1 Surface mounted multilayer ceramic capacitor construction

DIMENSION




Fig. 2 Surface mounted multilayer ceramic capacitor dimension

Table I

TYPE	CC0603	CC0805	CC1206	CC1210	CC1808	CC1812
L ₁ (mm)	1.6 ±0.10	2.0 ±0.20	3.2±0.20	3.2 ±0.20	4.5 ±0.30	4.5 ±0.30
W (mm)	0.8 ±0.07	1.25 ±0.20	1.6±0.20	2.5 ±0.20	2.0 ±0.30	3.2 ±0.30
T (mm)	Refer to table 2 to 7					
L ₂ /L ₃ (mm)	min.	0.20	0.25	0.25	0.25	0.25
	max.	0.50	0.75	0.75	0.75	0.75
L ₄ (mm)	min.	0.60	0.55	1.40	1.40	2.20

CAPACITANCE RANGE & THICKNESS FOR NP0 100V**Table 2** For NP0 100 V sizes from 0603 to 1812

CAPACITANCE (pF)	100 V 0603	0805	1206	1210	1808	1812
10						
12						
15						
18						
22						
27						
33						
39						
47						
56						
68						
82						
100	0.8 ±0.10	0.6 ±0.10				
120						
150			0.6 ±0.10			
180						
220						
270						
330						
390						
470						
560						
680						
820						
1,000						
1,200						
1,500		0.85 ±0.10				
1,800						
2,200				0.6 ±0.10	1.25 ±0.20	1.25 ±0.20
2,700						
3,300		1.25 ±0.20				
3,900			0.85 ±0.10			
4,700						
5,600			1.15 ±0.15	0.85 ±0.10		

Table 2 For NP0 100 V sizes from 0603 to 1812 (continued)

CAPACITANCE (pF)	100 V 0603	0805	1206	1210	1808	1812
6,800			1.15±0.15			
8,200				0.85 ±0.10		1.25 ±0.20
10,000			1.25 ±0.20			
12,000						
15,000				1.25 ±0.20		0.85 ±0.10
18,000						
22,000						1.15±0.15
27,000						
33,000						
39,000						
47,000						

NOTE

1. Values in shaded cells indicate thickness class in mm.
2. Capacitance range < 10 pF is on request.

CAPACITANCE RANGE & THICKNESS FOR NP0 200/250 V

Table 3 For NP0 200/250 V sizes from 0603 to 1812

CAPACITANCE (pF)	200/250 V 0603	0805	1206	1210	1808	1812
10						
12						
15						
18						
22						
27						
33						
39						
47	0.8 ±0.10	0.6 ±0.10	0.6 ±0.10			
56						
68						
82						
100						
120						
150						
180						

Table 3 For NP0 200/250 V sizes from 0603 to 1812 (continued)

CAPACITANCE (pF)	200/250 V	0603	0805	1206	1210	1808	1812
220							
270							
330	0.8 ±0.10		0.85 ±0.10				
390				0.6 ±0.10			
470							
560			1.25 ±0.20				
680							
820			0.8 ±0.10				
1,000				0.85 ±0.10			
1,200					1.25 ±0.20		
1,500			1.25 ±0.20	1.15±0.15			
1,800				0.8 ±0.10			1.25 ±0.20
2,200					0.85 ±0.10		
2,700						1.25 ±0.20	
3,300				1.25 ±0.20	1.15±0.15		
3,900							0.85 ±0.10
4,700					1.25 ±0.20		1.15±0.15
5,600							
6,800							
8,200							
10,000							

NOTE

1. Values in shaded cells indicate thickness class in mm.
2. Capacitance range < 10 pF is on request.

CAPACITANCE RANGE & THICKNESS FOR NP0 500 V

Table 4 For NP0 500 V sizes from 0805 to 1812

CAPACITANCE (pF)	500 V	0805	1206	1210	1808	1812
10						
12						
15	0.6 ±0.10		0.6 ±0.10			
18						
22						
27						

Table 4 For NP0 500 V sizes from 0805 to 1812 (continued)

CAPACITANCE (pF)	500 V 0805	1206	1210	1808	1812
33					
39					
47					
56					
68	0.6 ±0.10	0.6 ±0.10			
82					
100					
120					
150					
180			0.85 ±0.10		
220					
270					
330	0.85 ±0.10				
390					
470		0.85 ±0.10			
560					
680		1.15±0.15			
820	1.25 ±0.20				
1,000					
1,200		0.8 ±0.10	1.15±0.15		1.25 ±0.20
1,500					
1,800		1.25 ±0.20		1.25 ±0.20	
2,200			1.25 ±0.20		
2,700					1.15±0.15
3,300					
3,900					
4,700					1.25 ±0.20
5,600					
6,800					
8,200					
10,000					

NOTE

1. Values in shaded cells indicate thickness class in mm.
2. Capacitance range < 10 pF is on request.

CAPACITANCE RANGE & THICKNESS FOR X7R 100V

Table 5 For X7R 100 V sizes from 0805 to 1812

CAPACITANCE (pF)	100 V	0603	0805	1206	1210	1808	1812
100							
150							
220							
330							
470							
680							
1,000	0.8 ±0.10						
1,500							
2,200		0.6 ±0.10	0.85 ±0.10				
3,300							
4,700							
6,800							
10,000							
15,000							
22,000		0.85 ±0.10					
33,000							
47,000		1.25 ±0.20					0.85 ±0.10
68,000					0.85 ±0.10	1.25 ±0.20	
100,000			1.15±0.15				
150,000					1.15±0.15		
220,000					1.6 ±0.20		1.15±0.15
330,000							
470,000							1.6 ±0.20
680,000							
1,000,000							

NOTE

1. Values in shaded cells indicate thickness class in mm.

CAPACITANCE RANGE & THICKNESS FOR X7R 200/250 V**Table 6** For X7R 200/250 V sizes from 0805 to 1812

CAPACITANCE (pF)	200/250 V	0805	1206	1210	1808	1812
100						
150						
220						
330						
470						
680						
1,000	0.85 ±0.10					
1,500						
2,200						
3,300		0.85 ±0.10				
4,700						
6,800						
10,000	1.25 ±0.20					
15,000	0.8 ±0.10			0.85 ±0.10		
22,000	1.25 ±0.20					
33,000			1.15±0.15	1.15±0.15	1.25 ±0.20	
47,000						
68,000			1.25 ±0.20			
100,000				1.25 ±0.20		1.15±0.15
150,000						
220,000						1.6 ±0.20
330,000						2.0 ±0.20
470,000						
680,000						
1,000,000						

NOTE

1. Values in shaded cells indicate thickness class in mm.

CAPACITANCE RANGE & THICKNESS FOR X7R 500 V**Table 7** For X7R 500 V sizes from 0805 to 1812

CAPACITANCE (pF)	500 V 0805	1206	1210	1808	1812
100					
150					
220					
330					
470					
680					
1,000	0.8 ±0.10				
1,500					
2,200		1.15±0.15			
3,300					
4,700			1.15±0.15		0.85 ±0.10
6,800					
10,000	1.25 ±0.20	1.25 ±0.20		1.25 ±0.20	1.15±0.15
15,000					
22,000			1.25 ±0.20		
33,000		1.6 ±0.20			
47,000					1.25 ±0.20
68,000					
100,000					1.6 ±0.20
150,000					
220,000					
330,000					
470,000					
680,000					
1,000,000					

NOTE

1. Values in shaded cells indicate thickness class in mm.

THICKNESS CLASSES AND PACKING QUANTITY

Table 8

DESCRIPTION	SIZE CODE	THICKNESS CLASSIFICATION (mm)	8 mm TAPE WIDTH/AMOUNT PER REEL				12 mm TAPE WIDTH /AMOUNT PER REEL	
			Ø180 mm, 7"		Ø330 mm, 13"		Ø180 mm, 7" Blister	
			Paper	Blister	Paper	Blister		
Mid / High voltage	0603	0.8 ±0.10	4,000	---	---	---	---	---
	0805	0.6 ±0.10	4,000	---	---	---	---	---
		0.8 ±0.10	4,000	---	---	---	---	---
		0.85 ±0.1	4,000	---	---	---	---	---
		1.25 ±0.20	---	3,000	---	---	---	---
	1206	0.6 ±0.10	4,000	---	20,000	---	---	---
		0.8 ±0.10	4,000	---	---	---	---	---
		0.85 ±0.10	4,000	---	15,000	---	---	---
		1.00 ±0.10	---	3,000	---	10,000	---	---
		1.15 ±0.15	---	3,000	---	10,000	---	---
		1.25 ±0.20	---	3,000	---	---	---	---
	1210	0.6 ±0.10	---	4,000	---	15,000	---	---
		0.85 ±0.10	---	4,000	---	10,000	---	---
		1.15 ±0.15	---	3,000	---	10,000	---	---
		1.25 ±0.20	---	3,000	---	---	---	---
		1.6 ±0.20	---	2,000	---	---	---	---
	1808	1.15 ±0.15	---	---	---	---	---	1,500
		1.25 ±0.20	---	---	---	---	---	3,000
		1.35 ±0.15	---	---	---	---	---	1,000
		1.5 ±0.10	---	---	---	---	---	1,000
		1.6 ±0.20	---	---	---	---	---	2,000
		2.0 ±0.20	---	---	---	---	---	2,000
	1812	0.85 ±0.10	---	---	---	---	---	2,000
		1.15 ±0.15	---	---	---	---	---	1,500
		1.25 ±0.20	---	---	---	---	---	1,000
		1.35 ±0.15	---	---	---	---	---	1,000
		1.5 ±0.1	---	---	---	---	---	1,000
		1.6 ±0.2	---	---	---	---	---	1,000
		2.0 ±0.20	---	---	---	---	---	2,000

ELECTRICAL CHARACTERISTICS**NP0/X7R DIELECTRIC CAPACITORS; NISN TERMINATIONS**

Unless otherwise stated all electrical values apply at an ambient temperature of 20 ± 1 °C, an atmospheric pressure of 86 to 106 kPa, and a relative humidity of 63 to 67%.

Table 9

DESCRIPTION	VALUE
Capacitance range ⁽¹⁾	10 pF to 470 nF
Capacitance tolerance ⁽¹⁾ :	
NP0	±5%
X7R	±10%
Dissipation factor (D.F.) ⁽¹⁾ :	
NP0	≤ 0.1%
X7R	≤ 2.5%
Insulation resistance after 1 minute at U_r (DC)	$R_{ins} \geq 10 \text{ G}\Omega$ or $R_{ins} \times C \geq 500$ seconds whichever is less
Maximum capacitance change as a function of temperature (temperature characteristic/coefficient):	
NP0	±30 ppm/°C
X7R	±15%
Operating temperature range:	
NP0/X7R	−55 °C to +125 °C

NOTE

1. NP0: frequency = 1 MHz for $C \leq 1 \text{ nF}$, measuring at voltage 1 V_{rms} ; frequency = 1 KHz for $C > 1 \text{ nF}$, measuring at voltage 1 V_{rms}
 X7R: frequency = 1 KHz for $C \leq 10 \text{ }\mu\text{F}$, measuring at voltage 1 V_{rms} .

TESTS AND REQUIREMENTS

Table 10 Test condition, procedure and requirements

TEST	TEST METHOD	PROCEDURE	REQUIREMENTS
Mounting	IEC 60384-21/22	4.3 The capacitors may be mounted on printed-circuit boards or ceramic substrates	No visible damage
Visual inspection and dimension check		4.4 Any applicable method using $\times 10$ magnification	In accordance with specification
Capacitance		4.5.1 NP0: $f = 1 \text{ MHz}$ for $C \leq 1 \text{ nF}$, measuring at voltage $1 V_{\text{rms}}$ at 20°C ; $f = 1 \text{ KHz}$ for $C > 1 \text{ nF}$, measuring at voltage $1 V_{\text{rms}}$ at 20°C X7R: $f = 1 \text{ KHz}$ for $C \leq 10 \mu\text{F}$, measuring at voltage $1 V_{\text{rms}}$ at 20°C	Within specified tolerance
Dissipation factor (D.F.)		4.5.2 NP0: $f = 1 \text{ MHz}$ for $C \leq 1 \text{ nF}$, measuring at voltage $1 V_{\text{rms}}$ at 20°C ; $f = 1 \text{ KHz}$ for $C > 1 \text{ nF}$, measuring at voltage $1 V_{\text{rms}}$ at 20°C X7R: $f = 1 \text{ KHz}$ for $C \leq 10 \mu\text{F}$, measuring at voltage $1 V_{\text{rms}}$ at 20°C	In accordance with specification
Insulation resistance		4.5.3 At U_r (DC) for 1 minute	In accordance with specification
Voltage proof		4.5.4.2 Test voltage (DC) applied for 1 minute $U_r \leq 100 \text{ V}$: $2.5 \times U_r$ applied to NP0/X7R series $100 \text{ V} < U_r \leq 200 \text{ V}$: $1.5 \times U_r + 100 \text{ V}$ applied to NP0/X7R series $200 \text{ V} < U_r \leq 500 \text{ V}$: $1.3 \times U_r + 100 \text{ V}$ applied to NP0/X7R series $U_r > 500 \text{ V}$: $1.3 \times U_r$ applied to NP0/X7R series I : 7.5 mA	No breakdown or flashover
Temperature characteristic		4.6 Between minimum and maximum temperature	NP0: $\Delta C/C$: 30 ppm/ $^\circ\text{C}$ X7R: $\Delta C/C$: 15%
Adhesion		4.15 A force applied for 10 seconds to the line joining the terminations and in a plane parallel to the substrate for size ≥ 0603 : a force of 5 N applied for size 0402: a force of 2.5 N applied	No visible damage

Table 10 Test condition, procedure and requirements (continued)

TEST	TEST METHOD	PROCEDURE	REQUIREMENTS
Bond strength of plating on end face	IEC 60384-21/22	4.8 Mounting in accordance with IEC 60384-22 paragraph 4.3 Conditions: bending 1 mm at a rate of 1 mm/s, radius jig 340 mm	No visible damage NP0: $\Delta C/C_i \leq 1\%$ or 0.5 pF whichever is greater X7R: $\Delta C/C_i \leq 10\%$
Resistance to soldering heat	4.9	Precondition: 150 +0/-10 °C for 1 hour, then keep for 24 ± 1 hours at room temperature Preheating: for size ≤ 1206: 120 to 150 °C for 1 minute Preheating: for size > 1206: 100 to 120 °C for 1 minute and 170 to 200 °C for 1 minute Solder bath temperature: 260 ± 5 °C Dipping time: 10 ± 0.5 seconds Recovery time: 24 ± 2 hours.	The termination shall be well tinned NP0: $\Delta C/C_i \leq 0.5\%$ or 0.5 pF whichever is greater X7R: $\Delta C/C_i \leq 10\%$ D.F.: within initial specified value R _{ins} : within initial specified value
Solderability	4.10	Unmounted chips completely immersed in a solder bath at 235 ± 5 °C Dipping time: 2 ± 0.5 seconds Depth of immersion: 10 mm	The termination shall be well tinned.
Rapid change of temperature	4.11	Preconditioning: 150 +0/-10 °C for 1 hour, then keep for 24 ± 1 hours at room temperature 5 cycles with following detail: 30 minutes at lower category temperature; 30 minutes at upper category temperature Recovery time 24 ± 2 hours.	No visual damage NP0: $\Delta C/C_i \leq 1\%$ or 1 pF whichever is greater X7R: $\Delta C/C_i \leq 15\%$ D.F.: within initial specified value R _{ins} : within initial specified value
Damp heat, with U _r load	4.13	Initial measurements; after 150 +0/-10 °C for 1 hour, then keep for 24 ± 1 hours at room temperature Duration and conditions: 500 ± 12 hours at 40 ± 2 °C; 90 to 95% RH; U _r applied Final measurement: perform a heat treatment at 150 +0/-10 °C for 1 hour, final measurements shall be carried out 24 ± 1 hours after recovery at room temperature without load.	NP0: $\Delta C/C_i \leq 2\%$ or 1 pF whichever is greater X7R: $\Delta C/C_i \leq 15\%$ NP0: D.F.: 2 × initial value max. X7R ≥ 100 V: D.F. ≤ 5% NP0: R _{ins} ≥ 2,500 MΩ or R _{ins} × C _r ≥ 25 seconds, whichever is less X7R: R _{ins} ≥ 500 MΩ or R _{ins} × C _r ≥ 25 seconds, whichever is less

Table 10 Test condition, procedure and requirements (continued)

TEST	TEST METHOD	PROCEDURE	REQUIREMENTS
Endurance	IEC 60384-21/22 4.14	Preconditioning; Initial measurements; after 150 +0/-10 °C for 1 hour, then keep for 24 ± 1 hours at room temperature Duration and conditions: 1,000 ± 12 hours at upper category temperature with 1.5 × U_r voltage applied Final measurement: perform a heat treatment at 150 +0/-10 °C for 1 hour; final measurements shall be carried out 24 ± 1 hours after recovery at room temperature without load.	NP0: $\Delta C/C_i \leq 2\%$ or 1 pF whichever is greater X7R: $\Delta C/C_i \leq 15\%$ NP0: D.F.: 2 × initial value max. X7R ≥ 100 V: D.F. ≤ 5% NP0: $R_{ins} \geq 4,000 \text{ M}\Omega$ or $R_{ins} \times C_r \geq 40$ seconds, whichever is less X7R: $R_{ins} \geq 1,000 \text{ M}\Omega$ or $R_{ins} \times C_r \geq 50$ seconds, whichever is less

REVISION HISTORY

REVISION	DATE	CHANGE NOTIFICATION	DESCRIPTION
----------	------	---------------------	-------------

Version 0	Sep 08, 2005	-	- New
-----------	--------------	---	-------