


FB9B



Series	FB
Material Name	FB9
Feature	La/Co added
Application	Automotive Grade
Status	 Production



Magnetic Characteristics	
Residual Magnetic Flux Density [Br] / mT	450 ±10
Coercive Force [Hcb] / (kA / m)	342.2 ±12
Coercive Force [Hcj] / (kA / m)	358.1 ±12
Maximum Energy Product [BH] / (kJ / m³)	38.6

! Images are for reference only and show exemplary products.
! This PDF document was created based on the data listed on the TDK Corporation website.
! All specifications are subject to change without notice.