


FB3G



Series	FB
Material Name	FB3
Feature	General material
Application	Sensor Application
Status	Production



Magnetic Characteristics	
Residual Magnetic Flux Density [Br] / mT	375 ±15
Coercive Force [Hcb] / (kA / m)	254.6 ±12
Coercive Force [Hcj] / (kA / m)	270.6 ±20
Maximum Energy Product [BH] / (kJ / m³)	25.9

! Images are for reference only and show exemplary products.
! This PDF document was created based on the data listed on the TDK Corporation website.
! All specifications are subject to change without notice.