
Creation Date : July 29, 2019 (GMT)

Neodymium Magnets

NEOREC40UH

Lead Free

Series	NEOREC
Material Name	40UH
Feature	General material
Application	Commercial Grade Industrial equipment Automotive Grade
Temperature_Classification	140°C
Status	Production



Magnetic Characteristics	
Residual Magnetic Flux Density [Br] / mT	1290 ±30
Coercive Force [Hcb] / (kA / m)	995 ±56
Coercive Force [Hcj] / (kA / m)	1990 Min.
Maximum Energy Product [BH] / (kJ / m³)	310 ±16

! Images are for reference only and show exemplary products.
! This PDF document was created based on the data listed on the TDK Corporation website.
! All specifications are subject to change without notice.

Copyright(c) TDK Corporation. All rights reserved.