

High Loss, Low Density, Flexible, Carbon-loaded, Silicone Rubber Sheet

FLEXIBLE CARBON-LOADED SILICONE RUBBER SHEET

Eccosorb JCS is a carbon-loaded, silicone rubber sheet. It obtains its microwave properties via a carbon loading system and is therefore electrically conductive. Eccosorb JCS is waterproof and has excellent thermal characteristics, tolerating high and low temperatures. Low out-gassing is assumed, but formal testing has not been completed yet. Material does not flake or shed. Complex shapes are best cut with a water jet system.

FEATURES AND BENEFITS

- High loss
- Low density
- Very flexible
- Dust free
- High frequency applications

MARKETS

- Automotive
- Telecom
- Industrial

SPECIFICATIONS

| TYPICAL PROPERTIES | ECCOSORB JCS |
|-----------------------------|----------------------------------|
| Frequency range | 6 – 100 GHz |
| Service Temperature °C (°F) | -70 to 177 (-94 to 350) |
| Thickness | 0.50 mm - 3.18mm (0.020"-0.125") |
| Color | Black |

Data for design engineer guidance only. Observed performance varies in application. Engineers are reminded to test the material in application.

ELECTRICAL PROPERTIES

Eccosorb JCS is a pure dielectric absorber with no magnetic properties (permeability = 1). The complex permittivity varies with frequency, see graphs below. Attenuation is a figure of merit for the lossiness of absorbent material and should not be used to directly estimate insertion loss.

Insertion loss is defined as the reduction in energy between point A and point B caused by the insertion of a material. In general, insertion loss is a function of the material electromagnetic parameters and the thickness. JCS can be custom tailored to many different insertion loss values.

| | Attenuation (dB/cm) | |
|-------|---------------------|--------|
| | 3 GHz | 10 GHz |
| JCS-3 | 2 | 3.5 |
| JCS-5 | 4.5 | 9 |
| JCS-7 | 8 | 16 |
| JCS-9 | 10 | 20 |


APPLICATIONS

- Eccosorb JCS is used to lower cavity Q's in RF amplifiers, oscillators, cabinets containing microwave devices, computer housings, LNB's, and isolation of antennas by insertion loss.
- Eccosorb JCS is also used to reduce surface currents on radiating elements and outer ground-plane type surfaces.


AVAILABILITY

- Standard sheets are 30.5 cm x 30.5 cm (12"x12")
- Standard thicknesses are 0.50 mm – 3.18 mm (0.20"-0.125") with the exception of JCS-9 which has a maximum thickness of 2.03 mm (0.08")
- Eccosorb JCS can also be supplied with a Pressure Sensitive Adhesive (PSA) Product designation 'ECCOSORB® JCS-X/SS6M'.
- Eccosorb JCS is available in other sizes and customer specified configurations upon request.


Typical attenuation of
ECCOSORB JCS-7




JCS-X Insertion Loss @3GHz



JCS Permittivity (e')



JCS Permittivity (e'')



RFP-DS-JCS 081015

Any information furnished by Laird and its agents is believed to be accurate and reliable. All specifications are subject to change without notice. Responsibility for the use and application of Laird materials rests with the end user, since Laird and its agents cannot be aware of all potential uses. Laird makes no warranties as to the fitness, merchantability or suitability of any Laird materials or products for any specific or general uses. Laird, Laird Technologies, Inc or any of its affiliates or agents shall not be liable for incidental or consequential damages of any kind. All Laird products are sold pursuant to the Laird Technologies' Terms and Conditions of sale in effect from time to time, a copy of which will be furnished upon request. © Copyright 2015 Laird Technologies, Inc. All Rights Reserved. Laird, Laird Technologies, the Laird Logo, and other marks are trademarks or registered trademarks of Laird Technologies, Inc. or an affiliate company thereof. Other product or service names may be the property of third parties. Nothing herein provides a license under any Laird or any third party intellectual property rights.