



## DISSIPATIVE PINK POLY



### Specifications:

#### Electrical Properties

Static Decay  
 Surface Resistance  
 Polycarbonate Haze  
 Corrosivity Observations

#### Typical Values

<1.0 sec.  
 < 10<sup>11</sup> Ohms  
 NE  
 NE

#### Test Procedures/Method

ASTM 101 Method 4046  
 ESD S11.11  
 72 hr contact  
 MIL-STD-3010, M3005

#### Physical Properties


Thickness  
 Melt Index  
 Density  
 Dart Impact  
 Coefficient of Friction  
 1% Secant Modulus (Stiffness)

4 mils  
 0.050 gm/10 min  
 0.923 gm/cc  
 230 gms  
 MD 24,000 psi  
 MD 25,000 psi

ASTM D-1238  
 ASTM D-1505  
 ASTM D-1709  
 ASTM D-1894 (unmodified film)  
 ASTM D-882

Item No.	Size (in.) W x L	Item No.	Size (in.) W x L
49100	2 x 3	49110	8 x 12
49101	3 x 4	49111	10 x 12
49102	3 x 5	49112	10 x 14
49103	4 x 6	49113	10 x 20
49104	5 x 7	49114	12 x 16
49105	5 x 8	49115	14 x 16
49106	6 x 8	49116	15 x 18
49107	6 x 9	49117	16 x 20
49108	6 x 10	49118	18 x 20
49109	8 x 10	49119	18 x 24

Packaged 100 per package



Made in America

#### RoHS Compliance Statement

None of the following materials are intentionally added in manufacturing this product: lead, mercury, cadmium, hexavalent chromium, polybrominated biphenyls (PBB) or polybrominated diphenyl ethers (PBDE) as outlined in the Directive 2002/95/EC Article 4.1. See Protektive Pak Inc. letter on-line at [ProtektivePak.com](http://ProtektivePak.com).

### TRANSPARENT STATIC DISSIPATIVE (PINK POLY)

# PROTEKTIVE PAK

PROTEKTIVE PAK  
 13520 MONTE VISTA AVENUE, CHINO, CA 91710  
 PHONE (909) 627-2578, FAX (909) 363-7331  
[ProtektivePak.com](http://ProtektivePak.com)

**DRAWING NUMBER**  
 49100

**DATE:**  
 5/06