


NEOREC47HF



<b>Series</b>	NEOREC
<b>Material Name</b>	47HF
<b>Feature</b>	Dy Free
<b>Application</b>	Commercial Grade
<b>Temperature_Classification</b>	100°C
<b>Status</b>	Production



Magnetic Characteristics	
Residual Magnetic Flux Density [Br] / mT	1390 ±20
Coercive Force [Hcb] / (kA / m)	1058 ±48
Coercive Force [Hcj] / (kA / m)	1273 Min.
Maximum Energy Product [BH] / (kJ / m³)	366 ±16

! Images are for reference only and show exemplary products.  
! This PDF document was created based on the data listed on the TDK Corporation website.  
! All specifications are subject to change without notice.