



TO-5 Photocells

Plastic Encapsulated

Features


- Five Photoconductive Materials
- Tolerance: $\pm 40\%$ @ 1 ftc, $\pm 33\%$ @ 2 ftc

Description

The Silonex TO-5 series of photocells provide up to seven standard resistance ranges in CdS or CdSe materials. Most of these devices are also available in a hermetic package.

Absolute Maximum Ratings

Operating & Storage Temperature -60°C to $+75^{\circ}\text{C}$
 Power Dissipation @ 25°C (1) 125 mW



Electrical Characteristics ($T_A=25^{\circ}\text{C}$, source at 2854°K)

Silonex Part No	Sensitive Material	Spectral Peak (nm)	R @ 1 ftc (Kohms) (3)	R @ 2 ftc (Kohms) (3)	R _{TYP} @ 100 ftc (ohms)	Min. R _{DARK} (Mohms) (2)	V _{MAX} (Volts) (peak AC or DC)
NSL-4512	Type 4 CdS	515	43		1,000	2.5	120
NSL-4522			18.6		400	1.0	120
NSL-4532			8.0		230	0.40	120
NSL-4542			3.5		120	0.10	120
NSL-4552			330		8,000	20.0	320
NSL-4562			155		4,600	10.0	320
NSL-4572			65		3,800	4.0	320
NSL-5512	Type 5 CdS	550		3.3	300	0.22	120
NSL-5522				10	700	0.67	120
NSL-5532				165	10,000	11.0	320
NSL-5542				30	1,000	20.0	120
NSL-5552				30 (4)	1,000	10.0	120
NSL-5562				37.5 (5)	1,200	10.0	120
NSL-5572				47.5 (6)	2,000	1.0	120
NSL-6512	Type 6 CdSe	690		0.60	50	0.40	120
NSL-6522				1.2	100	0.80	120
NSL-6532				30	2,000	20.0	320
NSL-7512	Type 7 CdS	615		2.7	250	0.45	120
NSL-7522				5.4	500	0.90	120
NSL-7532				10	500	6.7	120
NSL-7542				100	5,000	67.0	250
NSL-7552				600	20,000	400.0	320

Specifications subject to change without notice.

103259 REV 2

Notes: (1) derate linearly to zero at 75°C .

(2) 5 sec. after removal of test light

(3) cells light adapted at 30 to 50 Ftc for 16 hrs minimum prior to electrical tests.

(4) $\pm 50\%$

(5) $\pm 60\%$

(6) $\pm 70\%$

2 Cogan Ave, Plattsburgh
 NY, 12901, USA
 Tel: 518-561-3160
 Fax: 514-747-3906

Northwich, Cheshire
 CW9 7TN, United Kingdom
 Tel: 01606-41999
 Fax: 01606-49706

2150 Ward, Montreal
 QC, H4M 1T7, Canada
 Tel: 514-744-5507
 Fax: 514-747-3906