

PIC-M0610 NdFeB Standard Magnet


Data

Material	NdFeB, Ni-coated	
Orientation	axially	
Remanence Br	mT	1150
Coercivity HcB	kA/m	840
Coercivity HcJ	kA/m	1075
Energy Product (BH) max.	kJ/m ³	255
Magnetic Moment M	x10 ⁻⁵ Vs cm	3.18
Operating Temperature max.	°C	85
Curie Temperature Tc	°C	310
Temperature Coefficient Tk(Br)	%/°C	-0.12
Density	g/cm ³	7.5

Nominal values unless otherwise specified

Dimensions

in mm



Customized types available.